



COMMERCIAL TESTING COMPANY

1215 South Hamilton Street • Post Office Box 985 • Dalton, Georgia 30722
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Standard Method of Test for
Critical Radiant Flux of Floor-Covering Systems
Using a Radiant Heat Energy Source

ASTM E 648-03

Imported Hardwood, Astronium Graveolens

Report Number 04-07216

Test Number 3585-1879

July 19, 2004

Tiger Deck, LLC
Wilsonville, Oregon

The ASTM E 648 flooring radiant panel operated by Commercial Testing Company is accredited by the United States Department of Commerce, National Institute of Standards and Technology (NIST), through the National Voluntary Laboratory Accreditation Program (NVLAP) for compliance with criteria set forth in NIST Handbook 150:2001, all requirements of ISO/IEC 17025:1999, and relevant requirements of ISO 9002:1994.

Commercial Testing Company

(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced test procedure, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.

TESTED TO BE SURE®

Since 1974

INTRODUCTION

This test report is a presentation of results of a flammability test on a material submitted by Tiger Deck, LLC, Wilsonville, Oregon. The test was conducted in accordance with the American Society for Test and Materials fire test response standard E 648-03, *Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source*. This method is sometimes referred to as the flooring radiant panel.

This test method is technically identical to the method described in NFPA Number 253. It measures the critical radiant flux at flame-out of horizontally mounted complete floor-covering systems that duplicate or simulate accepted installation practices. Tests on individual components are of limited value and are not valid for certification purposes.

This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of materials, products, or assemblies under actual fire conditions.

PURPOSE

The flooring radiant panel test measures the level of incident radiant heat energy at flame-out of a floor-covering system. It provides a basis for estimating one aspect of fire behavior of systems installed in corridors or exitways. Imposed radiant flux simulates thermal radiation levels likely to impinge on the floors of a building whose upper surfaces are heated by flames or hot gases, or both, from a fully developed fire in an adjacent room or compartment.

TEST PROCEDURE

A gas and air fueled radiant heat energy panel is mounted in the test chamber at a 30° angle to the horizontal plane of the specimen. The panel generates an energy flux distribution ranging along the length of the test specimen from a nominal maximum of 1.0 W/cm² to a minimum of 0.1 W/cm². Air flow through the chamber is controlled at a velocity of 250 feet per minute. The test is initiated using a gas pilot burner brought into contact with the specimen and extinguished after a specified time.

The floor-covering system, fully described in Table I, is tested in triplicate, each specimen measuring 20 cm wide by 100 cm long. Prepared specimens are conditioned a minimum of 96 hours in an atmosphere maintained at 71 ± 2°F and 50 ± 3% relative humidity. Chamber operating conditions are verified on the day of the test by measuring the flux level at the 40 cm mark. An incident flux level of 0.50 ± 0.02 W/cm² indicates proper operation and calibration of the test chamber.

Specimens are placed in the chamber and allowed to preheat for 5.0 minutes followed by a 5.0-minute application of the pilot burner. The specimens are allowed to burn until they self-extinguish, at which time they are removed from the test chamber and the farthest point of flame propagation measured. The critical radiant flux is determined from the flux profile determined during calibration of the test instrument.

TEST RESULT

The test result is presented as the average value of the three specimens tested expressed in terms of Critical Radiant Flux in units of W/cm². All pertinent individual specimen data are presented in Table II. The flux profile shown in the figure is typical of that determined during calibration of the flooring radiant panel instrument used for this test.

The general classification for the floor-covering system identified in this report is based on the NFPA 101 *Life Safety Code*. However, care must be exercised in its use as a material may be otherwise classified by the authority having jurisdiction.

TABLE I. FLOORING SYSTEM

Flooring:

Identification: Imported Hardwood, Astronium Graveolens
 Type Flooring: Hardwood Tongue/Groove Flooring
 Color: Natural
 Plank Size: 5-1/2 inches wide by 3/4 inch thick

Flooring System:

Installation: The flooring planks were assembled into T/G decks using three (3) 1/2-inch by 1-inch battens attached with 4d coated nails, two per plank.
 Subfloor: Simulated Concrete (Reinforced Cement Board)

TABLE II. TEST RESULT

Test Data	#1	#2	#3
Maximum Burn Distance (cm)	8.0	11.1	9.6
Time to Flame Out (min)	10.5	10.5	10.6
Critical Radiant Flux (W/cm ²)	>1.08	1.06	>1.08

Average Critical Radiant Flux >1.08 W/cm²

NFPA 101 Classification Type I

TYPICAL FLUX PROFILE

